



TECHNOVINYL POLYMERS(I)LTD.  
30, Unique Indl. Estate, Dr. Rajendra Prasad  
Road, Mulund(W), Mumbai-400 080  
Tel.: 022-25930940/41/43/44. Fax: 022-25642577  
Email: [kk\\_group@vsnl.net](mailto:kk_group@vsnl.net) Website: [www.kkthelittlegiant.com](http://www.kkthelittlegiant.com)



## TECHNICAL DATA SHEET

**Product Code No.: KPP 7073**

**Binary reinforced PP Composite  
For Door Panels of Automotive interiors**

Properties	Test Method	Unit	Value
MFR @ 230°C, 2.16 Kg.	ASTM D 1238	Gms/10 min	> 22
Specific gravity	ASTM D 792	g/cm <sup>3</sup>	0.99
Tensile Strength @ yield	ASTM D 638	Kg/cm <sup>2</sup>	440
Flexural Modulus	ASTM D 790	Kg/cm <sup>2</sup>	26500
Notched Izod Impact - at 23°C	ASTM D 256	Kg cm/cm	2.5
Rockwell Hardness		R-scale	116
HDT @ 0.46 N/mm <sup>2</sup>	ASTM D 648	Deg. C	138
Long term Heat Resistance		Deg. C	> 125
Shrinkage Value		%	< 1

### Features:

- High Stiffness
- Fast Moulding Cycles
- Very High Long term Heat Resistance
- Low Warpage
- UL 94 HB Class & cUL/RTI
- High Flow
- Low Impact
- High HDT
- **Scratch Resistance**
- High Surface Hardness
- High Crystallization Temperature

**Applications** – Door Panels for Automotive interiors

Manufactures Of :

Thermoplastic Elastomers  
Hi Performance PVC Compounds  
PP Compounds  
Speciality Polymers