



TECHNOVINYL POLYMERS(I)LTD.  
30, Unique Indl. Estate, Dr. Rajendra Prasad  
Road, Mulund(W), Mumbai-400 080  
Tel.: 022-25930940/41/43/44. Fax: 022-25642577  
Email: [kk\\_group@vsnl.net](mailto:kk_group@vsnl.net) Website: [www.kkthelittlegiant.com](http://www.kkthelittlegiant.com)



## TECHNICAL DATA SHEET

### Product Code No. 3070 K-FLEX THERMOPLASTIC ELASTOMERS For Welding Cable Jacketing

Original Physical Properties	Value	Unit
Specific Gravity	1.22	
Shore Hardness	67 ( $\pm$ 5)	Shore A
Tensile Strength	8 min.	MPa
Elongation at Break	> 400	%
<b>Compression Set</b>		
At Room Temp.	48	%
At 70°C	59	%
At 100°C	72	%
<b>Heat Ageing : 7 days at 100°C</b>		
Retained Tensile Strength	90	%
Retained Elongation	80	%
<b>Oil Ageing : 7 days at 100°C</b>		
Retained Tensile Strength	65	%
Retained Elongation	60	%

#### Characteristics:

- PVC/NBR Elastomer ionic cross linked
- Oil Resistance
- Heat Resistance
- Abrasion Resistance
- Matt Finish
- Acid, Alkali and chemical resistance
- Service temp. -20 deg C to +100 deg C

#### Processing Temperature:

140°C to 170°C

#### Manufactures Of :

Thermoplastic Elastomers  
Hi Performance PVC Compounds  
PP Compounds  
Speciality Polymers



TECHNOVINYL POLYMERS(I)LTD.  
30, Unique Indl.Estate, Dr.Rajendra Prasad  
Road, Mulund(W), Mumbai-400 080  
Tel.: 022-25930940/41/43/44. Fax: 022-25642577  
Email: [kk\\_group@vsnl.net](mailto:kk_group@vsnl.net) Website: [www.kkthelittlegiant.com](http://www.kkthelittlegiant.com)



## TECHNICAL DATA SHEET

### Product Code No. XL 70 K-PRENE PP/EPDM For Welding Cable Jacketing

Original Physical Properties	Value	Unit
Specific Gravity	0.94	
Hardness	67 ( $\pm$ 5)	Shore A
Tensile Strength	5 min.	MPa
Elongation at Break	> 500	%
<b>Compression Set</b>		
At Room Temp.	29	%
At 70°C	43	%
At 100°C	48	%
<b>Heat Ageing : 7 days at 125°C</b>		
Retained Tensile Strength	90	%
Retained Elongation	90	%
<b>Oil Ageing : 7 days at 100°C</b>		
Retained Tensile Strength	40	%
Retained Elongation	40	%

#### Characteristics:

- PP/EPDM Elastomer dynamic vulcanized
- Medium Oil Resistance
- Abrasion Resistance
- Matt Finish
- Heat Resistance
- Service Temp. -50 deg C to +125 deg C

#### Processing Temperature:

160°C to 190°C

#### Manufactures Of :

Thermoplastic Elastomers  
Hi Performance PVC Compounds  
PP Compounds  
Speciality Polymers